



TECHNICAL DATA SHEET No 835

SPRAY P 961 1K ETCH PRIMER

GENERAL TECHNICAL DESCRIPTION

Fast drying 1K adhesion promoter primer for all metallic surfaces

Paintable with all 1K and 2K primers and topcoats

Available in a variety of shades that can simulate E-Coat and OEM inner parts colors (e.g. inside trunk area)

SURFACE

Aluminium
Stainless Steel
Galvanised
Bare Metal

PRETREATMENT/CLEANING OF SUBSTRATE



Clean substrate using a soft cloth and 770 ANTISIL NORMAL / 771 ANTISIL FAST DEGREASER

Make sure the surface is first wiped dry and then air dried

PRODUCT APPLICATION



Shake well before using:
2 - 3 min



Spray at a distance of
20 - 30 cm, thinly applied
coats



5 min / 23°C (73°F)



2 - 3 coats approximately
20 - 30 microns



10 min / 23°C (73°F)



Overcoat with any HB
BODY Mix system



After use turn bottle
upside down and spray
out a small quantity,
for the cleaning of the
nozzle

FLASH POINT

-97°C / -206°F

SPECIFIC GRAVITY

0.95 g/cm³

SOLID CONTENT

(NO THINNER / REDUCER)

23% Weight

VOC (2004/42/EC)

This is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840g/L.
2004/42/IIIB(e)(840)840

THEORETICAL COVERAGE

-

CLEANING OF EQUIPMENT

-

REMARKS

- Do not apply over fillers
- Always try to use the product in accordance with the specifications provided
- Shake for 2 - 3 min after agitator ball has started to rattle
- After preparing the area to be painted ensure it to be free from dirt, wax, oil etc
- It is recommended to test on a similar surface for achieving the desired finishing result
- Optimum operating temperature range 10 - 25°C (50 - 77°F)

STORAGE SHELF LIFE

Store in a cool place (+5°C - +25°C) (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 36 months in unused original containers



Always wear protective
equipment



Follow the application
instructions mentioned
in this TDS

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

MARCH 2022